












960 SR ETACLEAR CLEARCOAT 2:1

ET960-SR01 1L, transparent
ET960-SR05 5L, transparent

	Product	2K scratch resistant acrylic clearcoat. High gloss, excellent durability and UV stability.
	Substrates	Apply on top of fully dry solvent and waterborne basecoats
	Surface Preparation	The use of tack cloth is recommended prior application
	Application Conditions	18-22° C
	Mixing	2:1 by volume with Etalon hardener ET995 normal, fast and extra fast
	Dilution	No dilution required
	Pot Life	1,5 hours at 20° C
	Application Viscosity	15-17 sec at 20° C Ford cup 4
	Spraying Equipment	Gravity feed spray gun 1.3mm
	Number of Layers	2 coats
	Flash off	5-10 min
	Coating Thickness	45-50 µm
	Drying	20 min at 60° C
	Drying with IR lamps	8-10 min
	VOC	2004/42/IIIE(840)<840
	Shelf life	12 months