












# 975 UHS AIRDRY CLEARCOAT 2:1

ET975-UHS01 1L  
ET975-UHS05 5L

	<b>Product</b>	Highly productive UHS air dried clear coat with perfect gloss. Easy and quick application.
	<b>Substrates</b>	Apply on top of fully dry solvent or water born base coats.
	<b>Surface Preparation</b>	The use of tack cloth is recommended prior application.
	<b>Application Conditions</b>	18-22 °C
	<b>Mixing</b>	2:1 by volume with Etalon hardener ET975-Hard
	<b>Dilution</b>	Acrylic reducer/thinner 0-5%
	<b>Pot Life</b>	45 min at 20°C
	<b>Application Viscosity</b>	RFU viscosity is 14-16s at DIN 4
	<b>Spraying Equipment</b>	Gravity feed gun - 1.3mm
	<b>Number of Layers</b>	1,5 coat                      2 coats
	<b>Flash off</b>	without flash off              3-5min
	<b>Coating Thickness</b>	40-50 microns                  50-60 microns
	<b>Drying</b>	60-70 min at 20°C 5-7 min at 60°C
	<b>Drying with IR lamps</b>	IR: 5-7min
	<b>VOC</b>	Compliant <420 g/l
	<b>Shelf life</b>	24 months