












ETAPRIME 5:1 HS ACRYL PRIMER

ET5500AF-08/G - 800ml, grey
 ET5500AF-08/B - 800ml, black
 ET5500AF-08/W - 800ml, white

	Product	2K acrylic high-build primer/filler. Thanks to good flow application of even 2-3 thick coats provides easy sanding properties. It can be used instead of sprayable putty on large panels covered with polyester body fillers.
	Substrates	Steel, old paint, body filler, OEM primers and fiberglass
	Surface Preparation	In case of application over body fillers and putties, dry sand with P180-P240. Clean and degrease thoroughly. Use tack cloth for heavy dust.
	Application Conditions	18-22° C
	Mixing	By volume 5:1 with Etalon ET5501 HN hardener
	Dilution	Acrylic reducer (thinner) 20-25%
	Pot Life	2 hours at 20° C
	Application Viscosity	25-30 sec Ford cup 4
	Spraying Equipment	Gravity feed spray gun 1.6-1.8mm
	Number of Layers	2-3 coats
	Flash off	10 min
	Coating Thickness	120-180 µm
	Drying	5-6 hours at 20° C or 30-45 min at 60° C
	Drying with IR lamps	15 min
	VOC	2004/42/IIIB©(540)<540
	Shelf life	12 months