










990 SR ETACLEAR CLEARCOAT 2:1

ET990-SR01 1L, transparent
ET990-SR05 5L, transparent

	Product	2K scratch resistant high solids acrylic clearcoat. Fast drying, non-yellowing UV resistant formula.
	Substrates	Apply on top of fully dry solvent and waterborne basecoats
	Surface Preparation	The use of tack cloth is recommended prior application
	Application Conditions	18-22° C
	Mixing	2:1 by volume with Etalon hardener ET991 slow and normal
	Dilution	No dilution required
	Pot Life	1,5 hours at 20° C
	Application Viscosity	14-16 sec at 20° C Ford cup 4
	Spraying Equipment	Gravity feed spray gun 1.3mm
	Number of Layers	2 coats
	Flash off	5-10 min
	Coating Thickness	45-50 µm
	Drying	15 min at 60° C
	Drying with IR lamps	7-10 min
	VOC	2004/42/IIIE(840)<840
	Shelf life	12 months