

# Etaglaze 1K-NC Fine Putty

gb 1/1215

page 1 / 1

## Product Information

Etaglaze 1K-NC Fine Putty is an one component fine putty on nitrocellulose base of good adhesion to iron, steel and hard, sanded old coatings.

Colour shade	grey		
Mixing ratio			
Hardener			
Thinners			
Spraying viscosity 20° C			
Application	spraying pressure	spraying nozzle	spraying operations
Air / Flowjar – Spray gun			
Airless / Airmix			
Pot life			
Coat thickness / dry film	max. 80 µm dry film per coat		
Curing time / Flash off time	consider a flash off time of approx. 1 h before the application of the next coat		
Dry	recoat time	dust dry	set to touch
Object Temp. 20° C	recoatable and sandable after 1 – 2 h.		
Object Temp. 60° C			
VOC-regulation	EC limiting value for the product (cat. B/e): 840 g/l (2007) This product contains max. 444 g/l VOC [ 3,7 lbs/gal]		

**Remarks :**

Degrease, derust and sand the substrate. Remove completely the old thermoplastic paintings. Then apply Etaglaze 1K-NC Fine Putty without any hardener. Avoid coat thickness more than 80 µm per coat and allow a cure time of approx. 1 h between the next coats. After drying Etaglaze 1K-NC Fine Putty may be sanded without any difficulty. Recoatable with all of the usual paint systems.

All products should be disposed of in relation to the regulations of the environmental health authorities. Protect your Environment!

This data sheet is for information purpose only! To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacture of our products. However the data is not binding and without warranty. Please follow recommendations stated on the relevant safety data sheet and precautions stated on the product label. We reserve our right to make additions, deletions, or modifications to the information at any time without prior notification.